

Analyzing the compressive strength of clinker mortars using approximate reasoning approaches – ANN vs MLR

Ahmet Beycioğlu^{*1}, Mehmet Emiroğlu^{1a}, Yilmaz Kocak² and Serkan Subaşı^{1b}

¹Civil Engineering Department, Technology Faculty, Düzce University, Düzce, Turkey

²Department of Construction, Vocational School of Technical Sciences, Dumlupınar University, Kutahya, Turkey

(Received February 3, 2014, Revised October 3, 2014, Accepted November 3, 2014)

Abstract. In this paper, Artificial Neural Networks (ANN) and Multiple Linear Regression (MLR) models were discussed to determine the compressive strength of clinker mortars cured for 1, 2, 7 and 28 days. In the experimental stage, 1288 mortar samples were produced from 322 different clinker specimens and compressive strength tests were performed on these samples. Chemical properties of the clinker samples were also determined. In the modeling stage, these experimental results were used to construct the models. In the models tricalcium silicate (C₃S), dicalcium silicate (C₂S), tricalcium aluminate (C₃A), tetracalcium alumina ferrite (C₄AF), blaine values, specific gravity and age of samples were used as inputs and the compressive strength of clinker samples was used as output. The approximate reasoning ability of the models compared using some statistical parameters. As a result, ANN has shown satisfying relation with experimental results and suggests an alternative approach to evaluate compressive strength estimation of clinker mortars using related inputs. Furthermore MLR model showed a poor ability to predict.

Keywords: clinker; prediction; compressive strength; artificial neural networks; multi linear regression

1. Introduction

Concrete is one of the most widely used construction material, owing to its good durability to cost ratio. The most important parameter on concrete performance is the properties of cement used in concrete production. Cement is the most produced and used binding material in the world with its 1.6 billion tons of annual production (Bilim 2011; Karakurt and Topçu 2011). Cement production has undergone a tremendous development from its beginnings some 2000 years ago. While the use of cement in concrete has a very long history, the industrial production of cements started in the middle of the 19th century, first with shaft kilns, which were later on replaced by rotary kilns as standard equipment worldwide (Schneider Romer *et al.* 2011). Portland cement is a binding material produced by grinding clinker with gypsum. Anhydrous Portland cement is essentially made of a synthetic rock, referred to as clinker, which contains at least four major

*Corresponding author, Ph.D, E-mail: abeycioglu@duzce.edu.tr

^aPh.D

^bPh.D

phases. These phases are tricalcium silicate (C_3S), dicalcium silicate (C_2S), tricalcium aluminate (C_3A) and tetracalcium alumina ferrite (C_4AF) (Neville 1981; Dunstetter de Noirfontaine *et al.* 2006).

Mineralogical and microstructure properties are mostly examined on coarse clinker particles and obtained results such as amount and dimension of mineral phases, porosity and some operational parameters of clinker manufacturing are usually dealt with clinker grind ability. Clinker or cement microstructure data could also help to predict cement service properties, particularly strength. But the combined effect of these micro structural parameters on strength should be considered otherwise the correlation may be low if these parameters are evaluated in isolation against compressive strength. It is apparent that several factors may play different roles together on service properties (Celik Oner *et al.* 2007).

Designers utilize principles of science and mathematics to develop specific technologies. These technologies are then used to create engineered tools such as products, structures, machines, processes or entire systems. It has already been seen that different tasks in engineering problem solving require different analysis (Krishnamoorthy and Rajeev 1996).

Nowadays, artificial intelligence methods are much popular in engineering sciences. One of the most popular artificial intelligence methods is ANN. ANN is a computational modeling method that tries to simulate the structure or functional aspects of biological neural networks. ANN can exhibit amazing capability in modeling the human brain. Generally, ANN model consists of a number of interconnected group of artificial neurons, each of which is fully connected to the other through connection weights. These weights, present the effect of an input parameter in the previous layer on the process element, can be adjusted to produce an output needed. ANN which is sometimes called as black-box modeling approach is an adaptive system that can be change its model according to relevant information that flows through the network during the learning phase. ANN can be used to model nearly any complex relationships between inputs and outputs in data (Duan Kou *et al.* 2013).

Recently, artificial neural networks has been extensively using in the fields of civil engineering applications especially cement and concrete properties estimation (Topçu and Sarıdemir 2008; Molero Segura *et al.* 2009; Özcan Atış *et al.* 2009; Sarıdemir 2009; Sarıdemir Topçu *et al.* 2009; Başyigit Akkurt *et al.* 2010; Erdem 2010; Önal and Öztürk 2010; Slonski 2010; Gencil Kocabas *et al.* 2011; Kyriazopoulos Anastasiadis *et al.* 2011; Nazari and Riahi 2011; Siddique Aggarwal *et al.* 2011; Alexandridis Triantis *et al.* 2012; Amani and Moeini 2012; Khan 2012; Madandoust Bungey *et al.* 2012; Öztürk and Turan 2012; Shah Alsayed *et al.* 2012; Triantis Stavarakas *et al.* 2012; Uysal and Tanyildizi 2012; Bal and Buyle-Bodin 2013; Boğa Öztürk *et al.* 2013; Duan Kou *et al.* 2013; Mashrei Seracino *et al.* 2013).

Alexandridis Triantis *et al.* (2012), presented a non-destructive method to predict the compressive strength of cement-based materials by studying the appearance of weak electrical signals (Kyriazopoulos Anastasiadis *et al.* 2011; Triantis Stavarakas *et al.* 2012) at specimens that are under mechanical stress. The result of their study showed that the ultimate compressive strength can be successfully predicted using ANN without destructive tests. The result of their study showed that the ultimate compressive strength can be successfully predicted using ANN without destructive tests. Önal O and Öztürk AU studied an artificial neural network analysis to establish a relationship between microstructural characteristics and compressive strength values of cement mortar. The developed model showed that a strong correlation between the microstructural properties of cement mortar and compressive strengths can be established by using ANN as non-linear statistical data modeling tool (Önal and Öztürk 2010). Sarıdemir developed two models (ANN and Fuzzy logic) to predict the compressive strength of mortars containing metakaolin at

the age of 3, 7, 28, 60 and 90 days. He used the data gathered from literature (179 specimens produced with 46 different mixture proportions). The results in the multilayer feed-forward neural networks developed in his research showed that neural networks system has strong potential for predicting compressive strength of mortars (Saridemir 2009). Nazari *et al* studied the multilayer feed forward neural networks and genetic programming to predict split tensile strength and percentage of water absorption of concretes containing TiO₂ nanoparticles. Result showed that neural network predicted better results (Nazari and Riahi 2011). Khan studied the applicability of artificial neural network for the prediction of compressive strength, tensile strength, gas permeability and chloride ion penetration of high performance composite cementitious systems. Results showed that results of developed model and experimental have a good correlation between each other (Khan 2012). Dantas *et al* developed an Artificial Neural Networks (ANNs) model for predicting the compressive strength, at the age of 3, 7, 28 and 91 days, of concretes containing Construction and Demolition Waste (CDW). They used a total of 1178 data to construct the models. The training and testing phases of their study strongly show the potential use of ANN to predict 3, 7, 28 and 91 days compressive strength of concretes containing CDW (Dantas Batista Leite *et al.* 2013).

In this presented paper, Artificial Neural Network (ANN) and Multiple Linear Regression (MLR) models were discussed to determine the compressive strength of clinker mortars. For constructing this models, 322 different mixtures with 1288 specimens of the 1, 2, 7 and 28 days compressive strength test results of clinker mortars, were used in training and testing. In training and testing of the models the input of C₃S, C₂S, C₃A, C₄AF, Blaine, specific gravity and age of samples were entered into the system while the output of compressive strength values were entered on the other hand. The model was trained with 201 experimental data results. Latterly, the remainders were used as only experimental input values for testing.

2. Experimental study

2.1. Specimens

The clinkers were produced in the Bursa Cement Factory (Turkey) and all experiments and analysis were performed in the factory. Chemical and physical analyses were conducted on samples used in the experiments. Chemical analyses of clinkers were performed on ARL 9900 X-ray workstation (XRF+XRD). Surface areas were determined as Blaine values by Toni Technik 6565 and specific gravity were determined by Quantachrome MVP-3. The results obtained from the chemical analyses of 322 different clinkers were given in Table 1.

Table 1 Chemical composition of clinkers

Chemical composition: wt.%	Minimum	Maximum	Chemical composition: wt.%	Minimum	Maximum
SiO ₂	18.67	21.58	Na ₂ O	0.19	0.53
Al ₂ O ₃	6.12	6.82	K ₂ O	0.01	0.75
Fe ₂ O ₃	3.29	3.96	Cl ⁻	0.005	0.06
CaO	64.85	68.06	Loss on ignition	0.23	0.45
MgO	0.77	1.54	Reactive CaO	0.36	3.22
SO ₃	0.24	1.05			

Table 2 The input and output parameters and quantities used in models.

Input parameters	Data used in training and testing the models	
	Minimum	Maximum
C ₃ S (%)	52.32	67.25
C ₂ S (%)	6.29	21.80
C ₃ A (%)	10.35	11.73
C ₄ AF (%)	10.01	12.05
Blaine (cm ² /g)	2810	3250
Specific gravity	3.12	3.27
Period of curing (Days)	1	28
Output value (MPa)	4	62.20

In the preparation of clinker mortar mixtures for compressive strength experiments, 450 g of clinker, 1350 g of standard sand and 225 ml of water were used in each mortar mixture according to TS EN 196-1. Prepared clinker mortars were poured into three-segmented 40x40x160 mm sized rectangular prism molds. Prepared samples were waited in the laboratory for 24 hours. At the end of 24-hour period, the samples were taken out of the molds and placed in water pools to get cured and prepared for the compressive strength experiments. Compressive strengths of each clinker mortars were measured at the end of 1, 2, 7 and 28 days using Atom Technic device. The minimum and maximum values of the experimental results used in modeling are given in Table 2.

4. Regression technique

Regression technique is the modelling of the relationship between 1 or more measured variables and another variable which is genuinely considered to be related to the measured variable(s). In the regression technique, the influencing variable (that is, the variable that causes an apparent change in the other variable) is called as explanatory variable (or independent variable) and the variable which is influenced by the independent variable (that is, affected by the apparent change caused by the independent variable) is called dependent variable (Kalaycı 2006). Regression models can be classified as linear and nonlinear models. However, nonlinear models can be transformed into linear models by various methods. To make a good prediction with the nonlinear regression models, you have to have preliminary information on the degree of the model or assume. The multiple linear regression model is an extension of a simple linear regression model to incorporate two or more explanatory variable in a prediction equation for a response variable. Multiple regression modeling is now a mainstay of statistical analysis in most fields because of it's power and flexibility (Brant 2007).

The formulation of the equations of multiple linear regression is given in Equation 1 (Subaşı 2009).

$$Y = b_0 + b_1X_1 + \dots + b_nX_n + \varepsilon \quad (1)$$

In model equation,

Y = Dependent variable

X_i = Independent variable

b_i = Calculated coefficient parameters

ε = Error term

5. Comparison criteria for the model

In the present study, the adequacy of the developed ANN model was evaluated by considering three statistical evaluation criteria. These statistical parameters are coefficient of determination (R^2) Eq. 2, Root Mean Squared Error (RMSE) Eq. 3 and Mean Absolute Errors (MAE) Eq. 4. Besides, the matching figures were drawn for both training and testing data to see relationship between model and experimental results.

$$R^2 = 1 - \frac{\left\{ \sum_{i=1}^n (y_{i(m)} - y_{i(p)})^2 \right\}}{\left\{ \sum_{i=1}^n (y_{i(m)} - y_{i(mean)})^2 \right\}} \quad (2)$$

$$RMSE = \sqrt{\frac{1}{N} \sum_{i=1}^n (y_{i(m)} - y_{i(p)})^2} \quad (3)$$

$$MAE = \frac{1}{N} \sum_{i=1}^N |Y_{i(m)} - Y_{i(p)}| \quad (4)$$

Here m is the measured values, p is the predicted values, $mean$ is the average measured values and N is the number of data. The statistical values of R^2 , RMSE and MAE for all the data sets are given related figures.

6. Developed ANN model structure, parameters and results

The ANN modeling consists of two steps: first step is to train the network; second step is to test the network with data, which were not used in training step. Neural networks have been trained to perform complex functions in various fields of application including pattern recognition, identification, classification, speech, vision and control systems (Terzi 2007)

ANN model developed in this research has seven neurons (variables) in the input layer and one neuron in the output layer as illustrated in Fig. 3. Some of the architectures with different number of neurons studied here in hidden layer/layers and their correlations with experimental results were investigated. The results of the comparison of the most successful ANN architectures tested in this study are given in Table 3. As seen in Table 3. minimum percentage error values were found through two hidden layer with 10 neurons of first layer and 5 neurons of second layer both training and testing sets.

While modeling networks, C_3S , C_2S , C_3A , C_4AF , blaine values, specific gravity and age of samples were used as inputs and the compressive strength of clinker samples was used as output. While modeling, 1087 samples were selected as training set and 201 data were selected as test set. The values of the training and test data were normalized between 0 and 1 using equation 5.

While modeling networks, C_3S , C_2S , C_3A , C_4AF , blaine values, specific gravity and age of samples were used as inputs and the compressive strength of clinker samples was used as output. While modeling, 1087 samples were selected as training set and 201 data were selected as test set. The values of the training and test data were normalized between 0 and 1 using Eq. 5.

Table 3 Comparison results of the most successful ANN models tested in this study

ANN architectures	7-8-6-1	7-9-5-1	7-9-6-1	7-10-3-1	7-10-5-1	7-10-5-1
R^2 (training)	0.78	0.84	0.85	0.92	0.98	0.94
R^2 (testing)	0.75	0.81	0.83	0.87	0.98	0.91

Table 4 The values of parameters used in model

Parameters	Values
Number of input layer neurons	7
Number of hidden layer	2
Number of first hidden layer neurons	10
Number of second hidden layer neurons	5
Number of output layer neuron	1

Table 5 The R^2 , MAE, RMSE statistics of comparison (ANN model and experimental results)

	Statistical parameters		
	R^2	MAE	RMSE
Training stage	0.98	1.50	1.93
Testing stage	0.98	1.74	2.26




Fig. 3 ANN model developed in this research

$$F = (F_i - F_{\min}) / (F_{\max} - F_{\min}) \quad (5)$$

In this equation F represents normalized value, F_i represents i . value of measured values and F_{\max} and F_{\min} represent maximum and minimum values of measured values.

Feedforward artificial neural networks (ANNs) are currently being used in a variety of applications with great success. The first main advantage of feedforward artificial neural networks is that they do not require a user-specified problem solving algorithm but instead they “learn” from examples, much like human beings. The second main advantage of feedforward artificial




Fig. 4 Matching of results for training set (ANN training)




Fig. 5 Relationship between measured and predicted compressive strengths (ANN training)




Fig. 6 Relationship between measured and predicted compressive strengths (ANN testing)

neural networks is that they possess an inherent generalization ability (Benardos and Vosniakos 2007).

In this study, the back-propagation learning algorithm was used in feed-forward with two hidden layer. Logarithmic sigmoid transfer function was used as the activation function for hidden layers and output layer. The learning rate and momentum are the parameters that affect the speed of convergence of the back-propagation algorithm. A learning rate of 0.001 and momentum 0.1 were fixed for selected network. The details of modeling parameters are given in Table 4.

The trained networks were used to run a set of test data. The ANN (7-10-5-1) has the best correlation with experimental results both training and testing sets. The representation of the network is as follow: in the model of 7-10-5-1, first number 7 represents the number of neurons in input layer, the number 10 represents the number of neurons in the first hidden layer, the number 5 represents the number of neurons in the second hidden layer and the last number 1 represents the number of neuron in output layer. Matching figure, correlation figure for training set and correlation figure for testing set are displayed in Figure 4-5-and 6, respectively. The R^2 , MAE and RMSE statistics obtained by comparing ANN model and experimental results by using Eq. 2,3 and 4 are presented in Table 5.

7. Statistical analysis and results

Tricalcium silicate, dicalcium silicate, tricalcium aluminate, tetracalcium alumina ferrite, blaine values, specific gravity and age of samples were selected as independent and the compressive strengths of clinker samples were selected as dependent variables to determine regression equation. A multiple linear regression (MLR) analysis was performed and an empirical correlation was developed to predict compressive strength of clinker mortars. In the model 1087 of 1288 experimental data selected for training the MLR analysis and 201 experimental data used for comparison of the experimental and statistical results. The resulting correlation at training stage is given in Eq. 6 and the regression model summary is listed in Table 6.




Fig. 7 Matching of results for training set (MLR training)




Fig. 8 Relationship between measured and predicted compressive strengths (MLR training)




Fig. 9 Relationship between measured and predicted compressive strengths (MLR testing)

Table 6 MLR model summary

Model	R	R ²	Adjusted R ²	Std. Error of the Estimate
1	0.894	0.800	0.792	8.81418
Coefficients ^a				
Model	Unstandardized coefficients		Standardized coefficients	
	B	Std. Error	Beta	
(Constant)	35.968	119.930		
C ₃ S	1.138	0.915	0.182	
C ₂ S	0.588	0.900	0.092	
C ₃ A	-2.935	2.856	-0.036	
C ₄ AF	4.351	1.974	0.082	
Blain	-0.005	0.008	-0.021	
Specific Gravity	-30.622	25.066	-0.043	
Age	1.555	0.057	0.883	
a. Predictors: (Constant), Age, Blaine, C ₂ S, Specific Gravity (SG), C ₃ A, C ₄ AF, C ₃ S				
b. Dependent Variable: Compressive Strength				

$$CS = 35.968 + 1.138 * C_3S + 0.588 * C_2S - 2.935 * C_3A + 4.351 * C_4AF - 0.005 * BL - 30.622 * SG + 1.555 * A \quad (6)$$

Table 7 The R^2 , MAE, RMSE statistics of comparison (MLR analysis and experimental results)

	Statistical parameters		
	R^2	MAE	RMSE
Training stage	0.77	7.21	8.96
Testing stage	0.79	7.12	8.64

Where; CS is compressive strength (MPa), C_3S is tricalcium silicate, C_2S is dicalcium silicate, C_3A is tricalcium aluminate, C_4AF is tetracalcium alumina ferrite, BL is blaine values, SG is specific gravity and A is age of samples. Experimental compressive strength values were compared with the predicted values obtained from Eq. 1. (Figs. 7-8-9). The R^2 , MAE and RMSE statistics obtained by comparing MLR analysis and experimental results by using Eq. 2,3 and 4 are presented in Table 7.

8. Conclusions

The potential of the Artificial Neural Network (ANN) and well known statistical method Multiple Linear Regression (MLR) technique were discussed for estimation the compressive strength of clinker mortars cured for 1, 2, 7 and 28 days. While developing the models 1087 experimental data (randomly selected) were used for training and 201 experimental data (the residual data) were used for testing. When comparing the prediction results and the experimental results in the training stage of ANN model, R^2 , RMSE and MAE were found as 0.98, 1.93 and 1.50 respectively. In addition, these values were found as 0.77, 8.96 and 7.21 for comparing the MLR and experimental results in the training stage. Similarly comparisons were done at the test stage and R^2 , RMSE and MAE were found as 0.98, 2.26 and 1.74 for ANN-Exp. comparison and 0.79, 8.64 and 7.12 for MLR-exp comparison respectively. Also, many unacceptable errors were seen when the matching figure evaluated for MLR-exp comparison especially 1 and 7 days results. According to the results, it can be concluded that MLR is not appropriate to use for this kind of application. When the results evaluated for ANN model, the results obtained from ANN model were very close to the experimental results.

As a result, this study shows that ANN can be used as a practical method for predicting the compressive strength values of clinker mortars cured for 1, 2, 7 and 28 days by using C_3S , C_2S , C_3A , C_4AF , blaine values, specific gravity and age of samples as inputs.

Acknowledgments

The authors express their gratitude to Bursa Cement Plant executives and director of quality control Sabiha KAN for their invaluable contributions on this study.

References

- Alexandridis, A. Chondrodima, E. and Sarimveis, H. (2013), "Radial basis function network training using a nonsymmetric partition of the input space and particle swarm optimization", *IEEE T. Neur. Networ.*, **24**(2), 219-230.
- Alexandridis, A. Triantis, D. Stavrakas, I. and Stergiopoulos, C. (2012), "A neural network approach for compressive strength prediction in cement-based materials through the study of pressure-stimulated electrical signals", *Construct. Build. Mater.*, **30**(0), 294-300.
- Amani, J. and Moeini, R. (2012), "Prediction of shear strength of reinforced concrete beams using adaptive neuro-fuzzy inference system and artificial neural network", *Scientia Iranica*, **19**(2), 242-248.
- Atici, U. (2011), "Prediction of the strength of mineral admixture concrete using multivariable regression analysis and an artificial neural network", *Exp. Syst.Appl.*, **38**(8), 9609-9618.
- Bagheri, M., Mirbagheri, S.A., Ehteshami, M. and Bagheri, Z. (2014), "Modeling of a sequencing batch reactor treating municipal wastewater using multi-layer perceptron and radial basis function artificial neural networks", *Process Safety and Environmental Protection* (In Press).
- Bal, L. and Buyle-Bodin, F. (2013), "Artificial neural network for predicting drying shrinkage of concrete", *Construct. Build. Mater.*, **38**(0), 248-254.
- Başıyigit, C., Akkurt, I., Kilincarslan, S. and Beycioglu, A. (2010), "Prediction of compressive strength of heavyweight concrete by ANN and FL models", *Neural Comput.*, **19**(4), 507-513.
- Benardos, P.G. and Vosniakos, G.C. (2007), "Optimizing feedforward artificial neural network architecture", *Eng. Appl. Artif. Intel.*, **20**(3), 365-382.
- Bilgehan, M. (2011), "A comparative study for the concrete compressive strength estimation using neural network and neuro-fuzzy modelling approaches", *Nondestructive Testing Evaluation*, **26**(1), 35-55.
- Bilhan, O., Emiroglu, M.E. and Kisi, O. (2011), "Use of artificial neural networks for prediction of discharge coefficient of triangular labyrinth side weir in curved channels", *Adv. Eng. Softw.*, **42**(4), 208-214.
- Bilim C. (2011), "Properties of cement mortars containing clinoptilolite as a supplementary cementitious material", *Construct. Build. Mater.*, **25**(8), 3175-3180.
- Boğa, A.R., Öztürk, M. and Topçu, İ.B. (2013), "Using ANN and ANFIS to predict the mechanical and chloride permeability properties of concrete containing GGBFS and CNI", *Compos. Part B: Eng.*, **45**(1), 688-696.
- Brant, R. (2007) Lecture notes <http://stat.ubc.ca/~rollin/teach/BiostatW07/reading/MLR.pdf>
- Celik, I.B., Oner, M. and Can, N.M. (2007), "The influence of grinding technique on the liberation of clinker minerals and cement properties", *Cement Concrete Res.*, **37**(9), 1334-1340.
- Dantas, ATA., Batista Leite, M. and de Jesus Nagahama, K. (2013), "Prediction of compressive strength of concrete containing construction and demolition waste using artificial neural networks", *Construct.Build. Mater.*, **38**(0), 717-722.
- Duan, Z.H., Kou, S.C. and Poon, C.S. (2013), "Prediction of compressive strength of recycled aggregate concrete using artificial neural networks", *Construct.Build. Mater.*, **40**(0), 1200-1206.
- Dunstetter, F., de Noirfontaine, M.N. and Courtial, M. (2006), "Polymorphism of tricalcium silicate, the major compound of Portland cement clinker: 1. Structural data: review and unified analysis", *Cement Concrete Res.*, **36**(1), 39-53.
- Erdem, H. (2010), "Prediction of the moment capacity of reinforced concrete slabs in fire using artificial neural networks", *Adv. Eng. Softw.*, **41**(2), 270-276.
- Gencil, O., Kocabas, F., Gok, M.S. and Koksall, F. (2011), "Comparison of artificial neural networks and general linear model approaches for the analysis of abrasive wear of concrete", *Construct. Build. Mater.*, **25**(8), 3486-3494.
- Hou, T-H., Su, C-H. and Chang, H-Z. (2008), "Using neural networks and immune algorithms to find the optimal parameters for an IC wire bonding process", *Exp. Syst. Appl.*, **34**(1), 427-436.
- Kalaycı, Ş. (2006), *Multi varied statistical techniques and SPSS applications*, Asil Publishing, Ankara (In

- Turkish).
- Karakurt, C. and Topçu, İ.B. (2011), “Effect of blended cements produced with natural zeolite and industrial by-products on alkali-silica reaction and sulfate resistance of concrete”, *Construct. Build. Mater.*, **25**(4), 1789-1795.
- Khan, M.I. (2012), “Mix proportions for HPC incorporating multi-cementitious composites using artificial neural networks”, *Construct. Build. Mater.*, **28**(1), 14-20.
- Khan, M.I. (2012), “Predicting properties of high performance concrete containing composite cementitious materials using artificial neural networks”, *Auto. Construct.*, **22**(0), 516-524.
- Khayet, M. and Cojocar, C. (2012), “Artificial neural network modeling and optimization of desalination by air gap membrane distillation”, *Sep. Purif. Technol.*, **86**(0), 171-182.
- Krishnamoorthy, C.S. and Rajeev, S. (1996), *Artificial Intelligence and Expert Systems for Engineers*, Taylor and Francis.
- Kyriazopoulos, A., Anastasiadis, C., Triantis, D. and Brown, C.J. (2011), “Non-destructive evaluation of cement-based materials from pressure-stimulated electrical emission – Preliminary results”, *Construct. Build. Mater.*, **25**(4), 1980-1990.
- Liang, X.B. and Wang, J. (2000), “A recurrent neural network for nonlinear optimization with a continuously differentiable objective function and bound constraints”, *IEEE T. Neur. Networ.*, **11**(6), 1251-1262.
- Lim, S.P. and Haron, H. (2013), “Cube Kohonen Self-Organizing Map (CKSOM) Model With New Equations in Organizing Unstructured Data”, *IEEE T. Neur. Networ.*, **24**(9), 1414-1424.
- Madandoust, R., Bungey, J.H. and Ghavidel, R. (2012), “Prediction of the concrete compressive strength by means of core testing using GMDH-type neural network and ANFIS models”, *Comput. Mat. Sci.*, **51**(1), 261-272.
- Mashrei, M.A., Seracino, R. and Rahman, M.S. (2013), “Application of artificial neural networks to predict the bond strength of FRP-to-concrete joints”, *Construct. Build. Mater.*, **40**(0), 812-821.
- Mohanraj, M., Jayaraj, S. and Muraleedharan, C. (2012), “Applications of artificial neural networks for refrigeration, air-conditioning and heat pump systems—A review”, *Renew. Sust. Energ. Rev.*, **16**(2), 1340-1358.
- Molero, M., Segura, I., Izquierdo, M.A., Fuente, J.V. and Anaya, J.J. (2009), “Sand/cement ratio evaluation on mortar using neural networks and ultrasonic transmission inspection”, *Ultrasonics*, **49**(2), 231-237.
- Nazari, A. and Riahi, S. (2011), “Prediction split tensile strength and water permeability of high strength concrete containing TiO₂ nanoparticles by artificial neural network and genetic programming”, *Compos.Part B: Eng.*, **42**(3), 473-488.
- Neville, A.M. (2006), *Properties of concrete*: Pearson Education limited, England.
- Önal, O. and Öztürk, A.U. (2010), “Artificial neural network application on microstructure–compressive strength relationship of cement mortar”, *Adv. Eng. Softw.*, **41**(2), 165-169.
- Öztürk, A.U. and Turan, M.E. (2012), “Prediction of effects of microstructural phases using generalized regression neural network”, *Construct. Build. Mater.*, **29**(0), 279-283.
- Özcan, F., Atiş, C.D., Karahan, O., Uncuoğlu, E. and Tanyildizi, H. (2009), “Comparison of artificial neural network and fuzzy logic models for prediction of long-term compressive strength of silica fume concrete”, *Adv. Eng. Softw.*, **40**(9), 856-863.
- Pintér, J.D. (2012), “Calibrating artificial neural networks by global optimization”, *Exp. Syst.Appl.*, **39**(1), 25-32.
- Sahoo, A.K., Zuo, M.J. and Tiwari, M.K. (2012), “A data clustering algorithm for stratified data partitioning in artificial neural network”, *Exp. Syst. Appl.*, **39**(8), 7004-7014.
- Sarıdemir, M. (2009), “Predicting the compressive strength of mortars containing metakaolin by artificial neural networks and fuzzy logic”, *Adv. Eng. Softw.*, **40**(9), 920-927.
- Sarıdemir, M., Topçu İ.B., Özcan, F. and Severcan, M.H. (2009), “Prediction of long-term effects of GGBFS on compressive strength of concrete by artificial neural networks and fuzzy logic”, *Construct. Build. Mater.*, **23**(3), 1279-1286.
- Schneider, M., Romer, M., Tschudin, M. and Bolio, H. (2011), “Sustainable cement production—present

- and future”, *Cement Concrete Res.*, **41**(7), 642-650.
- Shah A.A., Alsayed S.H., Abbas, H. and Al-Salloum, Y.A. (2012), “Predicting residual strength of non-linear ultrasonically evaluated damaged concrete using artificial neural network”, *Construct. Build. Mater.*, **29**(0), 42-50.
- Siddique, R., Aggarwal, P. and Aggarwal, Y. (2011), “Prediction of compressive strength of self-compacting concrete containing bottom ash using artificial neural networks”, *Adv. Eng. Softw.*, **42**(10), 780-786.
- Slonski, M. (2010), “A comparison of model selection methods for compressive strength prediction of high-performance concrete using neural networks”, *Comput. Struct.*, **88**(21-22), 1248-1253.
- Subaşı, S. (2009), “Prediction of mechanical properties of cement containing class C fly ash by using artificial neural network and regression technique”, *Scientific Research Essays*, **4**(4) 289:297.
- Terzi, S. (2007), “Modeling the pavement serviceability ratio of flexible highway pavements by artificial neural networks”, *Construct. Build. Mater.*, **21**(3), 590-593.
- Topçu, İ.B. and Sarıdemir, M. (2008), “Prediction of rubberized mortar properties using artificial neural network and fuzzy logic”, *J. Mater. Process. Technol.*, **199**(1-3), 108-118.
- Triantis, D., Stavrakas, I., Kyriazopoulos, A., Hloupis, G. and Agioutantis, Z. (2012), “Pressure stimulated electrical emissions from cement mortar used as failure predictors”, *Int. J. Fracture*, **175**(1), 53-61.
- Uysal, M. and Tanyildizi, H. (2012), “Estimation of compressive strength of self compacting concrete containing polypropylene fiber and mineral additives exposed to high temperature using artificial neural network”, *Construct. Build. Mater.*, **27**(1), 404-414.